


Description

**BOPP film white,
heat sealable with a low sealing threshold,
with activation on one side,
for printing, lamination and packaging,
in cases requiring protection from UV light and
lower heat sealing temperatures**



Properties		Unit	Limit	Method	Value					
Thickness		µm	±5%	ISO 4591, 4593 GOST 17035	15	20	25	30	35	
Density		g/cm ³	±10%	WATERFALL PRO	0,93					
Weight m ²		g/m ²	±5%	GOST 13199	13,95	18,60	23,25	27,90	32,55	
Tensile strength	MD	N/mm ² (Мпа)	not less	ASTM D882 ISO 527 GOST 14236	110			120		
	TD				220			230		
Elongation at break	MD	%	not more	ASTM D1894 GOST 27492	200					
	TD				70					
Kinetic coefficient of friction		UT / UT	-	ASTM D1894 GOST 27492	0,25					
Shrinkage at 120°C, 5 мин	MD	%	not more	ASTM D1204	4					
	TD				2					
Heat sealing strength at 95°C, 1 бар, 1 sec.		UT / UT	N/15 mm	not less	ASTM F88/F88M, D882 ISO 527					
Minimal heat sealing temperature not less than 1H/15mm at 1 бар, sec.		UT / UT	°C	-	WATERFALL PRO					
Haze		-	%	not more	ASTM D1003 GOST R 8.829	60	50	45	40	35
Gloss		T	%	not less	ASTM D2457	45				
Surface tension		T	mN/m (dyn/cm)	not less	ASTM D2578 ISO 8296	38				
MD – machine direction TD – transverse direction		T – treated side UT – untreated side								

Main characteristics

- low heat sealing temperature
- all white non-transparent appearance
- stable low coefficient of friction
- very high UV light protection of packaged goods

Application

- for flexible packaging of products which require protection from UV-light: ice cream, chocolate, flour, curd products, sweets and etc.
- for the production of wrap-around bottle labels in the original films form or in lamination

For packing

- on the high-speed HFFS and VFFS packaging machines
- with hot (heat sealing) seal formation at lower temperatures (from 85°C) and cold (using cold glue)
- Flow-Pack

For lamination

- with other films and materials using solvent or non-solvent (extrusive) lamination method
- with method of the solvent or nonsolvent (extrusion) lamination

For printing

- high-quality rotogravure and flexographic print
- with the use of solvent paint

Storage

- films should be stored on the pallets in a closed dry place and should not be exposed to direct sunlight, at a safe distance of not less than 1 m from heating devices or anything that can cause damage the package
- the film should be kept in workplace not less than 48 hours before being used
- guaranteed storage period – 6 months from production date

Treatment

- the guaranteed period for maintaining the minimum permissible level of surface tension on the activated film surface from the date of manufacture, subject to proper storage conditions, is 6 months
- in the interests of minimizing the deterioration of surface dressing level, it is recommended to store the film at a temperature of no higher than 30°C and use it in a short time

Recycling

- in the process of printing and lamination it is recommended to perform corona treatment

Reeling

- maximum roll diameter 800 mm
- film width in a roll from 290 to 2000 mm
- diameter of paper cores (inside) 76, 152 mm

Attention! Information specified in this document is for reference only; it contains averaged technical characteristics of Waterfall Pro LLC products based on results of laboratory tests performed in Waterfall Pro LLC standard operation conditions. Waterfall Pro LLC gives no representations and/or warranties and is expressly relieved from any liability for infringement of any third parties' intellectual property rights arising from processing of Waterfall Pro LLC products.

Testing of Waterfall Pro LLC products in order to determine their suitability in terms of meeting specific objectives of a person intending to purchase Waterfall Pro LLC products is the sole responsibility of such a person who shall be responsible for any consequences related to processing and use of Waterfall Pro LLC products.

This document does not constitute a quotation and its provision to any person shall not create any rights and duties on the part of Waterfall Pro LLC.